

Isoparfire® elegant .L

Pannelli parete in fibra minerale con fissaggio nascosto con certificazione FM
Concealed fastening mineral fibre wall panel with FM certification

ISOPARFIRE® ELEGANT.L è un pannello pensato per essere utilizzato su pareti che devono essere sicure e belle da vedere. Presenta una classe di reazione al fuoco A2-s1,d0 in quanto realizzato in fibra minerale; inoltre, si distingue per i suoi elementi di fissaggio nascosti in modo che i pannelli sulle pareti sembrano applicati senza soluzione di continuità. È rivestito in due supporti di acciaio zincato preverniciato, o, a scelta, acciaio inox o alluminio naturale preverniciato.


Prodotto negli spessori:

50-60-80-100-120-150-172-200-220-240 mm.
(spessore acciaio 0,6 + 0,6 mm)

ISOPARFIRE® ELEGANT.L is a panel designed to be used on walls that need to be safe and look good. It features class A2-s1, d0 fire reaction as it is made of mineral fibre; in addition, it stands out for its concealed fasteners so that the panels on the walls look seamlessly applied. It is coated in two backings of pre-painted galvanized steel, stainless steel or pre-painted natural aluminium.

Available thickness:

50-60-80-100-120-150-172-200-220-240 mm.
(steel thickness 0,6 + 0,6 mm)



spessore acciaio 0,6+0,6 mm
steel thickness 0,6 + 0,6 mm

$\lambda = 0,039 \text{ Watt/mK}$

U trasmittanza transmittance	50	60	80	100	120	150	172	200	220	240
W/m ² K	0,72	0,61	0,47	0,38	0,32	0,25	0,22	0,19	0,17	0,16
Kcal/m ² h °C	0,62	0,52	0,40	0,32	0,27	0,22	0,19	0,16	0,14	0,13

$\lambda = 0,041 \text{ Watt/mK}$

U trasmittanza transmittance	50	60	80	100	120	150	172	200	220	240
W/m ² K	0,76	0,64	0,49	0,39	0,33	0,27	0,23	0,20	0,18	0,17
Kcal/m ² h °C	0,65	0,55	0,42	0,33	0,28	0,23	0,20	0,17	0,15	0,14

▲ A RICHIESTA CON DENSITÀ DA 120 a 150 kg/m³. DENSITY FROM 120 to 150 kg/m³ ON REQUEST

